

MS Isolation

Dialinas S.A.

Adhesive and sealant based on SMP with very low density. It is suitable if at the same time a warmth or coldness isolation as well as reduction of sound and/or vibrations has to be achieved. Due to the extraordinary low density of 0.38g/cm³ a significant weight saving can be realised. Thanks to its compressibility this product is suitable for compression joints.

Product advantages

- Very low density
- Low thermal conductivity
- Noise insulating and vibration damping
- Compressible
- Simple processing
- Tolerance compensating
- Permanently elastic and stress compensating
- Free of solvents, isocyanates and silicones

Technical data

Chemical base	Silane modified polymer
Consistency, DIN EN ISO 7390	stable
Mechanism of curing	1 comp. moisture curing
Shore-A-hardness, DIN 53505	32
Modulus elongation at 100%, DIN 53504 S2 *	ca. 1.0 N/mm ²
Elongation at break, DIN 53504 S2 *	ca. 100%
Tensile strength, DIN 53504 S2 *	ca. 1.0 N/mm ²
Tooling time	max. 5 min.
Curing rate after 24h	≥ 3.5 mm
Curing rate after 48h	≥ 5.5 mm
Density	0.38 ± 0.05 g/cm ³
Volume change, DIN EN ISO 10563	≤ 2%
Temperature resistance after curing	- 40 °C to + 90 °C
Application temperature	+ 5 °C to + 40 °C

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

* The data are based on measurements after 7 days.

Application

Filling, spackling, isolate from voids, cracks, holes, connections and terminations in the area of construction. Squeeze type sealants in casing lids. Note: The adhesive and sealant is classified as a inflammable building material (building material class F according to DIN EN 13501-1) and may only be used if it is connected with another building material in such a way that the component is no longer inflammable.

Substrate range

Suitable materials are metals, powder-coated, varnished, galvanised, anodised, chromed or hot zinc dipped surfaces, various plastics, ceramics, stone, concrete and wood. Due to the large variety of different plastics and compositions as well as materials which are susceptible to cracks, preliminary tests are recommended.

Technical data sheet MS Isolation

Substrate preparation

To achieve reproducible results the substrate has to be pre-treated according to the state of technology. All undefined surfaces must be removed using suitable methods. Apply the adhesive/sealant promptly to the prepared surface. Depending on the substrate and the expected requirements a mechanical or chemical pre-treatment is recommended respectively cleaning with rubbing alcohol, isopropyl or acetone. For application the surface has to be clean, durable and free of dust, oil and grease. The compatibility with adjacent materials, coatings etc. must be determined in advance.

Adhesion promoter

With most materials a good adhesion is achieved even without adhesion promoter. In the case of high moisture influence we recommend our Adhesion Promoter V40 on non-porous materials, Adhesion Promoter V21 on open porous materials. For thermo-painted or powder-coated surfaces and plastic materials we recommend our Adhesion Promoter V40. Preliminary tests are recommended.

Processing

- Cut the nozzle tip according to the joint width
- Apply the material bubble free into the joint
- The joint must be applied within the tooling time
- Non-cured sealant can be removed with rubbing alcohol or isopropyl
- Cured sealant can only be removed mechanically

Paint compatibility

Due to the diversity of varnishes and paints on the market we recommend preliminary tests. Using paints based on alkyd resins may delay the drying process. If applied on painted or plastered substrates a sufficient drying time of the paint / plaster must be kept (in general 10 days). After cleaning with acetone joints can be varnished at any time.

Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons

Shelf life and storage conditions

- Shelf life depending on packaging
- Store cool and dry (10 - 25 °C)
- Further information on request

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

merz+benteli ag

Freiburgstrasse 616
CH - 3172 Niederwangen
Phone +41 31 980 48 48
Fax +41 31 980 48 49
info@merz-benteli.ch
www.merz-benteli.ch

Last Update: 31.07.2020

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical characteristics according to the Technical Data Sheets up to their expiry date which is available upon request and which is available on our website. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

